



SHRINKFLEX® 2:1 GLOSSY

ATTRACTIVE GLOSSY SURFACE · GOOD ELECTRICAL PROPERTIES EXCELLENT UV RESISTANCE

2:1 Glossy heatshrink tubing is the ideal way to create a tight, professional finish on any wire, hose or cable management project. Once shrunk, the tubing will hold its reduced state even in elevated temperatures. The wide range of diameters and the attractive glossy finish makes this heatshrink a perfect solution for any termination application. Not as versatile as a high ratio shrink product, 2:1 will still slide easily over small inline splices and connectors and provide a tight seal in many applications.

SIZING CHART


Nominal Size	Part #	Unshrunk Diameter /mm	Shrunk Diameter /mm	*Put-Ups		Available Colors	Lbs/ 100'
				M	L		
1/8"	H2G0.13	3.2	1.6	25'	500'	11	0.43
3/16"	H2G0.19	4.8	2.4	25'	200'	11	0.60
1/4"	H2G0.25	6.4	3.2	25'	200'	11	1.04
3/8"	H2G0.38	9.5	4.7	25'	200'	11	1.31
1/2"	H2G0.50	12.7	6.4	25'	200'	11	1.52
3/4"	H2G0.75	19.1	9.5	25'	100'	11	2.58
1"	H2G1.00	25.4	12.7	25'	100'	11	3.74
1 1/2"	H2G1.50	38.1	19.1	25'	100'	11	5.53
2"	H2G2.00	50.8	25.4	25'	100'	11	8.25

*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool

FEATURES


Material	Polyolefin
Grade	H2G
Monofilament Diameter	NA
Drawing Number	TF001H2G-WD
Cutting	Scissors

COLORS



Black (BK), Gray (GY), Clear (CL), White (WH), Yellow (YL), Orange (OR), Green (GN), Blue (BL), Purple (PP), Brown (BR), Red (RD)

CERTIFICATIONS



CHEMICAL RESISTANCE

Corrosion (ASTM DTL-23053)	No Corrosion
Fluid Resistance (73°F/23°C, 24 hrs.)	1,000
UV Color Stability (3,000 Hrs., Weather-o-meter)	No Color Reduction
UV Color Resistance (3,000 Hrs., Weather-o-meter)	No Color Reduction

PHYSICAL PROPERTIES


Monofilament Diameter (ASTM D-204)	NA
Flammability Rating	NA
Recommended Cutting	Scissors
Colors	11
Moisture Absorption (%) (ASTM D-570)	.2
Tensile Strength (psi) (ASTM D-638)	1,500
Elongation (%) (ASTM D-638)	200
Specific Gravity (ASTM D-792)	1.0
Low Temp. Flex (-67°F/-55°C) (MIL-DTL-23053)	No Cracking
Heat Resistance (277°F/136°C, 168 Hrs.) (ASTM D-638)	100
Secant Modulus (psi) (ASTM D-882)	25,000
Longitudinal Change (%) (MIL-DTL-23053)	+5, -15
Dielectric Strength (kV/mm) (ASTM D-876)	500
Volume Resistivity (ohm/cm) (ASTM D-876)	1.0 x 10 ¹⁵

FLAMMABILITY

Rating	NA
--------	----

OPERATING TEMPERATURES

Shrinks	239°F / 115°C
Maximum Continuous (Mil-I-23053)	221°F / 105°C
Minimum Continuous (Mil-I-23053)	-67°F / -55°C



HOW-TO

Measure the Shrinkflex® tubing to length and cut with a scissor. The thickness of your bundle, as well as the desired final appearance, will determine the length of the tubing you cut. Generally, a piece 1½" - 2" long will accommodate almost any need. Single wires, or smaller bundles, require shorter pieces.

Slip the Shrinkflex® tubing over the bundle and position it so that both the sleeved and unsleeved portions are sufficiently covered. Notice the small pieces of tubing installed on single wires as part of a color coding system. If your project requires multiple operations, always work up from the smallest to the largest bundle.

Gently apply heat to Shrinkflex® tubing from a heat gun, hair dryer or torch with an appropriate attachment. Keep the heat source far enough away so that hot metal or direct flame does not come in contact with the tubing, wires or sleeving. Move the heat around the bundle to prevent damaging the sleeving and to ensure that all areas of the tubing have been shrunk. Once cooled, your installation is complete.