



SHRINKFLEX® 4:1 POLYOLEFIN

SHRINKS TO 1/4 ITS ORIGINAL DIAMETER · EASILY INSTALLS OVER CONNECTORS & SPLICES VERSATILE AND ECONOMICAL TERMINATION SOLUTION

Shrinkflex® heatshrink tubing is the ideal way to create tight, professional finish on any wire, hose or cable management project. Once shrunk, the tubing will hold its reduced state even in elevated temperatures. 4:1 Heatshrink Tubing is the most versatile of the heatshrink products. The high shrink ratio ensures that the tubing will slip over large connectors or plugs and still provide a tight, professional seal.

SIZING CHART

Nominal Size	Part #	Unshrunk Diameter /mm	Shrunk Diameter /mm	*Put-Ups		Available Colors	Lbs/100'
				M	L		
1/2"	H4N0.50	12.0	3.0	25'	200'	1	1.17
3/4"	H3N0.75	19.0	4.5	25'	100'	1	2.75
1"	H3N1.00	25.4	7.0	25'	100'	1	3.25
1 1/4"	H3N1.50	32.0	8.0	25'	100'	1	4.00
1 1/2"	H3N2.00	38.0	9.5	25'	100'	1	4.25

Put-Ups: "M" = Shop Spool and "L" = Bulk Spool

FEATURES

Material	Polyolefin
Grade	H4N
Monofilament Diameter	NA
Drawing Number	TF001H4N-WD
Cutting	Scissors

COLORS



Black (BK)

CERTIFICATIONS



CHEMICAL RESISTANCE

Corrosion (ASTM DTL-23053)	No Corrosion
Fluid Resistance (73°F/23°C, 24 hrs.)	1,000

PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	NA
Flammability Rating	UL 224, VW-1
Recommended Cutting	Scissors
Colors	1
Tensile Strength (psi) (ASTM D-638)	1,500
Elongation (%) (ASTM D-638)	200
Moisture Absorption (%) (ASTM D-570)	.5
Specific Gravity (ASTM D-792)	1.35
Low Temperature Flex (-67°F/-55°C) (MIL-DTL-23053)	No Cracking
Heat Shock (482°F/250°C) (MIL-DTL-23053)	No Cracking
Heat Resistance (347°F/175°C, 168 hrs.) (ASTM D-638)	100
Secant Modulus (psi) (ASTM D-882)	25,000
Longitudinal Change (%) (MIL-DTL-23053)	±5
Dielectric Strength (volt/mil) (ASTM D-876)	500
Volume Resistivity (ohm/cm) (ASTM D-876)	1.0 x 10 ¹⁴

FLAMMABILITY

Rating	UL 224, VW-1
--------	--------------

OPERATING TEMPERATURES

Shrinks	194°F / 90°C
Melt Point (ASTM D-2117)	392°F / 200°C
Maximum Continuous (Mil-I-23053)	275°F / 135°C
Minimum Continuous (Mil-I-23053)	-67°F / -55°C


HOW-TO



Measure the Shrinkflex® tubing to length and cut with a scissor. The thickness of your bundle, as well as the desired final appearance, will determine the length of the tubing you cut. Generally, a piece 1½" - 2" long will accommodate almost any need. Single wires, or smaller bundles, require shorter pieces.



Slip the Shrinkflex® tubing over the bundle and position it so that both the sleeved and unsleeved portions are sufficiently covered. Notice the small pieces of tubing installed on single wires as part of a color coding system. If your project requires multiple operations, always work up from the smallest to the largest bundle.



Gently apply heat to Shrinkflex® tubing from a heat gun, hair dryer or torch with an appropriate attachment. Keep the heat source far enough away so that hot metal or direct flame does not come in contact with the tubing, wires or sleeving. Move the heat around the bundle to prevent damaging the sleeving and to ensure that all areas of the tubing have been shrunk. Once cooled, your installation is complete.

www.TECHFLEX.com

104 Demarest Road • Sparta, NJ 07871 • 1 (833) SLEEVEING • (973) 300-9242 • fax: (973) 300-9409

© 2023 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden. Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's® only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.

01-01-23