



**VINYL COATED FIBERGLASS - GRADE A**  
**CONFORMS WITH REQUIREMENTS OF MIL-I-3190/2**  
**RATED TO 266°F, CLASS H · RESISTS OILS, ACIDS & ALKALIES**

VINYL FLEX GLASS (VG) sleeving is a heat-treated, tightly braided fiberglass sleeving coated with a firmly bonded plasticized polyvinylchloride film. This durable sleeving will withstand mechanical stress and holds its dielectric strength on all bends. Vinyl Flex Glass is used for supplementary insulation on transformer, motor, generator, and resistor leads. Also other applications include television, radio, and other electric circuits where it can be pushed back to permit soldering. Highly resistant to acids and solvents, and will withstand tough assembly handling. The Vinyl compound is designed for continuous operation at 130°C temperatures, while providing excellent abrasion and cut-through resistance.

**SIZING CHART**

Nominal Size	Diameter	Part #	Grade	Wall Thickness	*Put-Ups		Available Colors	Lbs/ 100'
					M	L		
24	.020"	VGAG.24	A		250'	500'	3	
22	.025"	VGAG.22	A		250'	500'	3	
20	.032"	VGAG.20	A		250'	500'	3	
18	.040"	VGAG.18	A		250'	500'	3	
16	.053"	VGAG.16	A		250'	500'	3	
15	.057"	VGAG.15	A		250'	500'	3	
14	.064"	VGAG.14	A		250'	500'	3	
13	.072"	VGAG.13	A		100'	250'	3	
12	.081"	VGAG.12	A		100'	250'	3	
11	.091"	VGAG.11	A		100'	250'	3	
10	.102"	VGAG.10	A		100'	250'	3	
9	.114"	VGAG.09	A		100'	250'	3	
8	.129"	VGAG.08	A		100'	250'	3	
7	.144"	VGAG.07	A		100'	250'	3	
6	.162"	VGAG.06	A		100'	250'	3	
5	.182"	VGAG.05	A		100'	250'	3	
4	.204"	VGAG.04	A		100'	250'	3	
3	.229"	VGAG.03	A		100'	250'	3	
2	.258"	VGAG.02	A		100'	250'	3	
1	.289"	VGAG.01	A		50'	100'	3	
0	.325"	VGAG.00	A		50'	100'	3	
3/8"	.375"	VGA0.38	A		50'	100'	3	
7/16"	.438"	VGA0.44	A		50'	100'	3	
1/2"	.500"	VGA0.50	A		50'	100'	3	
5/8"	.625"	VGA0.63	A		50'	100'	3	
3/4"	.750"	VGA0.75	A		50'	100'	3	
7/8"	.875"	VGA0.88	A		50'	100'	3	
1"	1.00"	VGA1.00	A		50'	100'	3	

\*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool



# ELECTRICAL INSULATION

## Technical Data Sheet



### FEATURES

Material	Vinyl Coated Fiberglass
Grade	A (8,000V)
Wall Thickness	
Drawing Number	TF001VGA-WD
Cutting	Scissors

### COLORS



Black (BK), Yellow (YL), White (WH)

### CERTIFICATIONS



VW-1

### FLAMMABILITY

Rating	VW-1
--------	------

### OPERATING TEMPERATURES

Continuous Operation	266°F (130°C)
Low Temp Flexibility, Bends Without Cracking	-13°F / -25°C

### RATE OF BURNING

Conforms with requirements of NEMA TF-1, MIL-I-3190/3, and ASTM D372.

### CHEMICAL RESISTANCE

Resistant to oils, acids, alkalies and most organic solvents. After more than 168 hours in the most commonly used aromatics, xylene and toluene, the dried sleeving substantially regains its original properties.

[www.TECHFLEX.com](http://www.TECHFLEX.com)

104 Demarest Road • Sparta, NJ 07871 • 1 (833) SLEEVING • (973) 300-9242 • fax: (973) 300-9409

© 2023 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden. Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's® only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.

01-01-23