

VOLCANO[®] WRAP VOLCANIC ROCK TAPE MADE FROM CONTINUOUS FILAMENT BASALT FIBER PROTECTS UP TO 1,300°F · NON FLAMMABLE

Volcano[®] Wrap is made from continuous filament basalt fiber and is engineered for protection from temperatures 1,300°F. When wrapped around exhaust pipes, the unique construction creates attractive and durable finished product. Volcano[®] Wrap is 25% stronger and provides a 300°F increase in temperature protection over fiberglass wrap. The product is very rugged, and will not exhibit any vibration damage over long period of use. The volcanic rock fiber wrap is easy to install and will provide years of protection and good looks. Volcano[®] Wrap helps redirect the heat every race or every day in production, keeping engine areas cooler and performance results better.

SIZING CHART

	Width	Part #	Wall Thickness	*Put-Ups				Available	Lbs/
				XS	S	М	L	Colors	100'
	1"	VWN1.00	¹ / ₁₆ "	15'	25'	50'	100'	2	1.70
	2"	VWN2.00	¹ / ₁₆ "	15'	25'	50'	100'	2	3.20







ABRASION

Abrasion Resistance	LOW
Abrasion Test Machine	Taber 5150
Abrasion Test Wheel	Calibrase H-18
Abrasion Test Load	500g
Room Temperature	°F
Humidity	%
Material Destroyed - Braid Worn Through In Both Directions	203 Test Cycles
Pre-Test Weight	mg
Post-Test Weight	mg
Test End Loss Of Mass Point Of Destruction	mg

PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	NA
Flammability Rating	Non Flammable
Recommended Cutting	Scissors
Colors	2
Wall Thickness	.0625"

FLAMMABILITY

Rating	Non Flammable				
OPERATING TEMPERATURES					
Melt Point (ASTM D-2117)	2,642°F / 1,450°C				
Maximum Continuous (Mil-I-23053)	1,292°F / 700°C				
Minimum Continuous	°F / °C				
CHEMICAL RESISTANCE					
1=No Effect 2=Little Effect 3=Affected 4=More Affected 5=Severely Affected					
Aromatic Solvents	1				
Aliphatic Solvents	1				
Chlorinated Solvents	1				
Weak Bases	1				
Salts	1				
Strong Bases	1				
Salt Water (0-S-1926)	1				
Hydraulic Fluid (MIL-H-5606)	1				
Lube Oil (MIL-L-7808)	1				
De-Icing Fluid (MIL-A-8243)	1				
Strong Acids	2				
Strong Oxidants	2				
Esters/Ketones	1				
UV Light	2				
Petroleum	1				
Fungus (ASTM G-21)	1				
Halogen Free	Yes				
RoHS	Yes				
SVHC	None				

www.TECHFLEX.com

104 Demarest Road • Sparta, NJ 07871 • 1 (833) SLEEVING • (973) 300-9242 • fax: (973) 300-9409

© 2023 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden. Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex® only obligations are those in standard terms of sale for these products on typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.